



## LUBRIKO® RUST PREVENTATIVE # 1

### Description

**Lubriko® Rust Preventative # 1** is a solvent cutback, heavy film rust preventative designed for outdoor applications. The residual film, after solvent evaporation, is highly resistant to high humidity and salt environments.

### Usage

Cast iron parts coated with **Lubriko's Rust Preventative # 1** have been stored outdoors for three years without any signs of rusting. It can be applied by brush, spray or dipping. The dried film is a soft, waxy coating that can be removed by alkaline washer.

**Lubriko® Rust Preventative # 1** is an effective automotive rust proofing compound because of its excellent resistance to salt water and spray. It will afford long term rust protection indoors and out.

### Typical Properties

Brookfield Viscosity @ 21°C	3250
Total Base Number, mg KOH/gm, ASTM D-664	28
Specific Gravity @ 15.6°C ASTM D-1480	.88
Pounds per Gallon @ 15.6°C	7.33
Flash Point, deg. C, TCC	42.0
Nonvolatile, wt. %, ASTM D-2369	45-50
Colour	Dark Amber

Solids %	Film Thickness (ml)	5% Salt Spray <sup>1</sup> (Days/Fail)	Humidity Cabinet <sup>2</sup> (Days/Fail)
50	1.60	60+	60+
45	0.90	25	60+

1. Federal Standard 791B method 4001.2 using polished cold rolled steel panels.

2. ASTM D-1748 using polished cold rolled steel panels.

\*Note: To get 45% solids, add 10% by volume mineral spirits.

The information presented herein has been compiled from sources considered to be dependable and is accurate to the best of Commercial Oil Company's knowledge; however, the Commercial Oil Company makes no warranty whatsoever, expressed or implied, and expressly disclaims all liability for reliance thereon. Such data are offered solely for your consideration, investigation and verification.

35 BURFORD ROAD, HAMILTON, ONTARIO, CANADA L8E 3C6  
905-560-3244 • 1-800-463-1976 • FAX 905-560-2961 • [www.commercialoil.ca](http://www.commercialoil.ca)